



**SPECIAL PROVISIONS
FOR
HIGH FRICTION SURFACE TREATMENT**

**Pottawattamie County
IM-NHS-029-3(115)48--03-78**

**Effective Date
October 17, 2017**

THE STANDARD SPECIFICATIONS, SERIES 2015, ARE AMENDED BY THE FOLLOWING MODIFICATIONS AND ADDITIONS. THESE ARE SPECIAL PROVISIONS AND THEY SHALL PREVAIL OVER THOSE PUBLISHED IN THE STANDARD SPECIFICATIONS.

150347a.01 DESCRIPTION.

Construct a High-Friction Surface Treatment (HFST) on a hot-mix asphalt or Portland cement concrete pavement surface to restore or enhance the skid resistance.

150347a.02 MATERIALS.

A. General.

1. Prior to construction, provide certification for both the polymeric resin binder and aggregate that states the material meets the requirements listed in Tables 150347a.02-1 and 150347a.02-2.
2. Store all materials in a clean, dry environment and in accordance with the manufacturer's recommendations.
3. Obtain Material Safety Data Sheets (MSDS), Product Data Sheets, and other information pertaining to the safe practices for the storage, handling, and disposal of the materials, and to their health hazards. Provide a copy of this information to the Engineer.

B. Polymeric Resin Binder.

1. Polymeric resin binder components shall be packaged in suitable, well-sealed containers clearly labeled as to the type of material and the ratio of the components to be mixed by volume. Any special instructions regarding the mixing shall be included.
2. The label shall show resin or hardener components brand name, name of manufacturer, lot or batch number, temperature range for storage, expiration date, and the quantity contained therein.

3. The polymeric resin binder shall consist of a two-part thermosetting polymer resin compound which holds the aggregate firmly in position, and conforms to the following requirements:

Table 150347a.02-1: Epoxy Requirements

Property	Requirement	Test Method
Viscosity, Poises	7 - 30	ASTM D 2556
Gel Time, minutes	10 min.	AASHTO M 235, Class C
Ultimate Tensile Strength, psi	2500 – 5000	AASHTO M 235, Class C
Compressive Strength, psi	1000 min (3 hrs) 5000 min (7 days)	ASTM C 579
Water Absorption, %	1 max.	AASHTO M 235
Durometer Hardness (Shore D)	60 – 80	ASTM D 2240
Cure Rate (Dry through time), hours	3 max.	ASTM D 1640, 55 mils wet thickness
Elongation at Break Point, %	30 - 70	AASHTO M 235
Mixing Ratio	*	Per Manufacturer
Adhesive Strength, psi @ 24 hr.	250 min. or 100% substrate	ASTM D 4541

*Provide manufacturer's recommendations to Engineer prior to construction.

C. Aggregate.

Calcined bauxite material that is clean, dry, and free from foreign material and meets the following requirements. Deliver the calcined bauxite to the construction site in clearly labeled packaging that protects the aggregate from any contaminants on the job site and from exposure to rain or other moisture. The label shall show the name of the manufacturer and location of processing.

Table 150347a.02-2: Bauxite Aggregate Requirements

Property	Requirement	Test Method
Moisture Content, %	0.2 max.	AASHTO T 255
Aluminum Oxide, %	87 min.	ASTM C 25
LA Abrasion Test, %	20.0 max.	AASHTO T 96 (D Grading)
Aggregate Gradation <u>Sieve Designation</u>	<u>Percent Passing (Min.)</u>	AASHTO T 27
No. 4	100	
No. 6	95.0 – 100.0	
No. 16	0.0 – 5.0	

D. Equipment.

1. Truck Mounted Application Machine.

Use an approved self-propelled truck mounted application machine capable of continuously and thoroughly mixing polymeric resin binder components to the ratio recommended by the polymeric resin manufacturer at a minimum coverage rate of 15 gallons per minute. The machine shall include an aggregate drop spreader capable of mechanically continuously spreading bauxite aggregate at a minimum rate of 11 pounds per square yard in varying widths of up to 12 feet.

2. Portable Shot Blast Equipment.

Use approved portable shot blast equipment to remove curing compound and prepare Portland cement concrete surfaces prior to application of the polymeric resin.

3. Regenerative Air Sweeper.

Use a self-propelled Regenerative Air Sweeper (RAS) with power brooms capable of

cleaning the existing pavement and removing loose aggregate without dislodging the bonded HFST aggregate. The vacuum head shall have a minimum width of 6 feet and blast re-circulated, filtered air at a minimum rate of 20,000 cubic feet per minute. The RAS must be capable of recycling loose aggregate into clean, uncontaminated, and dry aggregate. The RAS must be capable of being used without water for dust suppression to ensure a dry surface will be maintained.

150347a.03 CONSTRUCTION.

A. Contractor Qualifications.

The Contractor that is placing the HFST shall provide documentation showing HFST or equivalent experience on at least three projects with similar state highway agencies.

B. Quality Control Plan.

1. Submit a Quality Control (QC) Plan to the Engineer for approval at least 30 days prior to paving. The QC Plan shall show proposed methods to control the equipment, materials, mixing, and paving operations to ensure conformance with these specifications. The QC Plan shall contain at a minimum the following information:
 - a. Key personnel and contact information.
 - b. List of manufacturer recommendations for storage of material, weather restrictions, curing time, and opening to traffic.
 - c. Cleaning and maintenance schedule for truck mounted application machine, including metering and monitoring devices.
 - d. Corrective actions that will be taken for unsatisfactory construction practices and deviations from specifications.
 - e. A technical expert representative from the polymeric resin manufacturer shall be present at the construction site to train construction personnel prior to placing the HFST and shall remain on the project for the first day of paving. After the first day, the representative shall be available during HFST application as necessary.
2. The QC Plan shall designate a QC Manager, who shall have full authority to institute any action necessary for the successful operation of this QC Plan. The QC Manager shall be on the jobsite at all times during placement of the HFST.
3. A field technician shall be present at the job site unless otherwise approved in the QC Plan. The field technician shall be responsible for the required field quality control sampling and testing in conformance with the approved quality control plan and contract documents. All sampling shall be performed in the presence of and in locations as directed by the Engineer. Maintain and make available upon request complete records of sampling, testing, actions taken to correct problems, and quality control inspection results. Any deviation from the approved QC Plan shall be cause for immediate suspension of the operations.

C. Weather Restrictions.

1. The polymeric resin binder material shall be applied on dry surfaces (including no condensation moisture from construction vehicles in front of the binder application), when the ambient temperature is 55° F and rising, unless the polymeric resin manufacturer can provide test data to support installations at lower temperatures; and the surface temperature below 100°F unless the aggregate can be installed within the working time specified at various surface temperatures by the manufacturer; or when the anticipated weather conditions or pavement surface temperature would not prevent the proper application of the surface treatment in accordance with the manufacturer's recommendations. Ensure the polymeric resin components are capable of being mixed at lower than ambient temperatures in the event that the components are stored

outdoors.

2. Do not place HFST materials when rain is forecast within 24 hours of application.
3. There shall be no visible moisture present on the surface of the pavement at the time of application of the HFST. A plastic sheet left taped in place for a minimum of 2 hours, according to ASTM D 4263, shall be used to identify moisture in the pavement.

D. Preparation.

1. Clean existing surfaces with a RAS without dust suppression water, or by other methods approved by the QC Manager and the Engineer prior to application of the polymeric resin. Surfaces may need to be washed with a mild detergent, and then rinsed and dried using a hot compressed air lance. Receiving surfaces must be clean, dry, and free of all dust, oil, debris, and any other material that might interfere with the bond between the polymeric resin binder material and existing surfaces.
2. Protect all utilities, drainage structures, curbs, and other items within or adjacent to the treatment location against the application of HFST materials.

E. Binder Application.

Mix the binder components proportionally in accordance with the manufacturer's recommended ratio. Apply the two-part polymeric resin base binder by a truck mounted application machine onto the pavement section to be treated within the temperature range specified in varying widths of up to 12 feet wide at a uniform application rate of 3.0 square yards per gallon, with a uniform thickness of 60 mils onto the pavement. Do not allow the binder to separate in the mixing lines, cure, dry, chill, set up, or otherwise impair retention bonding of the high friction surfacing aggregate. Ensure that no seams are visible in the middle of the traffic lanes of the finished work after application of the surface aggregate. The polymeric resin shall not be distributed and spread on the pavement with squeegees except for small irregular areas and tapers. Standing in the wet, uncured resin will result in that section of resin being removed and replaced at no cost to the Contracting Authority.

F. Aggregate Application.

Within approximately 4 seconds after placing the polymeric resin binder, apply the aggregate at a uniform rate of 11 to 15 pounds per square yard. Completely cover the "wet" polymeric resin binder with aggregate to achieve a uniform surface with no exposed polymeric resin wet spots remaining visible on the surface. A truck mounted application machine aggregate drop spreader must be used. Sprinkle or vertically drop the aggregate from a maximum height of 12 inches above the pavement surface without splashing the wet polymeric resin film during placement, whether by mechanical or manual means.

G. Curing and Clean-Up.

Allow the treatment to cure in accordance with polymeric resin manufacturer recommendations. Perform two separate clean-up processes by removing the excess aggregate with a RAS on the treated area and adjacent areas. Perform initial clean-up before opening to traffic. Perform secondary clean-up in coordination with the Engineer as needed.

H. Field Acceptance Testing.

Ensure that the coverage rate of the retained aggregate is 11 to 15 pounds per square yard. Remove and re-apply HFST where any patches of exposed polymeric resin exist or any other deficient areas as directed by the Engineer, at no additional cost to the Contract Authority.

150347a.04 METHOD OF MEASUREMENT.

The Engineer will measure the area of High Friction Surface Treatment placed in square yards.

150347a.05 BASIS OF PAYMENT.

Payment for High Friction Surface Treatment will be at the contract unit price per square yard. Payment is full compensation for the specified work, including preparation of the concrete surface (including joint sealing), furnishing and applying the polymeric resin, furnishing and applying the bauxite aggregate and any corrective action required.