



**SPECIAL PROVISIONS
FOR
COLORED CONCRETE PAVEMENT**

**Linn County
TAP-U-1187(799)--8I-57**

**Effective Date
September 21, 2021**

THE STANDARD SPECIFICATIONS, SERIES 2015, ARE AMENDED BY THE FOLLOWING MODIFICATIONS AND ADDITIONS. THESE ARE SPECIAL PROVISIONS AND THEY SHALL PREVAIL OVER THOSE PUBLISHED IN THE STANDARD SPECIFICATIONS.

157188.01 GENERAL REQUIREMENTS.

A. Description.

This work includes the finishing and construction of colored concrete pavement to the lines and grades shown on the plans including layout, subgrade preparation, forming, steel reinforcement, integral colored concrete, color curing and sealing agents, expansion joint material, color joint sealer, and all other incidental materials. The work shall include all labor, materials, equipment, and transportation required to install colored and tooled PCC pavement for both 4 inch and 8 inch thicknesses.

B. References.

1. American Concrete Institute (ACI)
 - a. ACI 301 "Specification for Structural Concrete for Buildings".
 - b. ACI 302 IR "Recommended Practice for Concrete Floor and Slab Construction".
 - c. ACI 303.1 "Standard Specification for Cast-In-Place Architectural Concrete".
 - d. ACI 304 "Recommended Practice for Measuring, Mixing, Transporting and Placing of Concrete".
 - e. ACI 305R "Recommended Practice for Hot Weather Concreting".
 - f. ACI 306R "Recommended Practice for Cold Weather Concreting".
2. American Society of Testing and Materials (ASTM):
 - a. ASTM C309 "Standard Specifications for Liquid Membrane Forming Compounds for Curing Concrete".
 - b. ASTM C494 "Standard Specification for Chemical Admixtures for Concrete".

- c. ASTM C979 "Standard Specification for Pigments for Integrally Colored Concrete".
- 3. American Association of State Highway and Transportation Officials (AASHTO):
 - a. AASHTO M194 "Chemical Admixtures".
- 4. National Ready Mixed Concrete Association (NRMCA):
 - a. CIP 5 "Plastic Shrinkage Cracking".

C. Submittals.

- 1. Product Data: Submit manufacturer's complete technical data sheets for the following:
 - a. Integral color concrete mixture.
 - b. Curing and sealing compound for integral colored concrete.
- 2. Design Mixes: For each type of concrete.
- 3. Samples for Initial Selection: Manufacturer's color charts showing proposed selection that complies with specified color match.
- 4. Qualification Data: or firms indicated in "Quality Assurance" Article, including list of completed projects.

D. Quality Assurance.

- 1. Manufacturer Qualifications: Manufacturer with 10 years of experience in manufacture of specified products.
- 2. Installer Qualifications: An installer with 5 years of experience with work of similar scope and quality.
- 3. Comply with the requirements of ACI 301.
- 4. Obtain each specified material from same source and maintain high degree of consistency in workmanship throughout Project.
- 5. Notification of manufacturer's authorized representative shall be given at least 1 week before start of Work.

E. Delivery, Storage, and Handling.

- 1. Deliver products in original factory unopened, undamaged packaging bearing identification of product, manufacturer, batch number, and expiration data, as applicable.
- 2. Store the product in a location protected from damage, construction activity, and precipitation in strict accordance with the manufacturer's recommendations.

F. Field Conditions.

- 1. Schedule placements to minimize exposure to wind and hot sun before curing materials are applied.
- 2. Avoid placing concrete if rain, snow, or if frost is forecasted within 24 hours. Protect fresh concrete from moisture and freezing.

3. Comply with professional practices described in ACI 305R and ACI 306R.
4. Schedule delivery of integral colored concrete to provide consistent mix times for batching until discharge. Mix times shall meet manufacturer's written recommendations.

G. Pre-Construction Conference.

Prior to placement of concrete, a meeting between Contractor, Engineer and Manufacturer's Representative shall be held to discuss the project and application methods.

157188.02 MATERIALS.

A. Products.

1. Cast-in-Place Concrete: Comply with requirements of Article 2301.02, B of the Standard Specifications.
2. Colored Admixture for Integrally Colored Concrete:
 - a. Scofield Chromix color additive C-34 Dark Gray. Contractor shall submit proposed color for Owner approval prior to purchasing product.
 - b. Admixture shall be a colored, water-reducing, admixture containing no calcium chloride with coloring agents that are lime proof and UV resistant.
 - c. Colored admixture shall conform to the requirements of ACI 303.1, ASTM C979, ASTM C494, and AASHTO M194.
 - d. Admixture shall be non-fading finely ground synthetic mineral-oxide coloring pigment and water reducing wetting agent.
3. Curing and Sealing Compound for Integrally Colored Concrete: Comply with ASTM C309 and ASTM 3315 for use with integrally colored concrete
 - a. Use to cure exterior flatwork that will be allowed to weather naturally with no or only occasional maintenance.
 - b. Clear, solvent-borne, non-yellowing and VOC compliant.
4. The use of products other than those specified will be considered providing that the Contractor requests its use in writing within 14 days prior to bid date. This request shall be accompanied by the following:
 - a. Certificate of compliance from material manufacturer stating that proposed products meet or exceed requirements of this Section.
 - b. Documented proof that proposed materials have a 10 year proven record of performance confirmed by at least five local projects that design professional can examine.

B. Concrete Mix Design.

1. Comply with requirements of Article 2301.02, B of the Standard Specifications.
2. Do not add calcium chloride to mix as it causes mottling and surface discoloration.
3. Supplemental admixtures shall not be used unless approved by manufacturer.
4. Do not add water to the mix in the field.
5. Add colored admixture to the mix according to manufacturer's written instructions in premeasured bags, not by weight or cement content.

157188.03 CONSTRUCTION.

A. Installation.

1. Examine subgrade and sub-base for compliance. Notify Engineer if conditions are noncompliant.
2. Steel reinforcement: Install in locations shown on the Plans. Elevate bar to achieve placement in middle (top to bottom) of concrete paving.
3. Move concrete into place with square-tipped shovels or concrete rakes.
4. Vibrators, when used, shall be inserted and withdrawn vertically.
5. Concrete shall be struck to specified level with wood or magnesium straight edge or mechanical vibrating screed.
6. Concrete surface shall be further leveled and consolidated with highway magnesium straight edge and/or magnesium bull float.
7. Mechanically float concrete surfaces as soon as concrete surface has taken its initial set and will support weight of a power float machine equipped with float shoes or combination blades and operator. Surface texture of roundabout paving shall match adjacent street surface. Surfaces adjacent to sidewalk paving shall match textures.

B. Integral Colored Concrete Paving.

1. Apply color release agent in accordance with manufacturer's recommendations.
2. Minor variations in appearance of colored concrete, which are similar to natural variations in color and appearance of uncolored concrete, are acceptable.

C. Curing and Sealing.

1. Protect concrete from prematurely drying and from excessive cold or hot temperatures that would alter normal curing process.
2. Integral Colored Concrete Paving:
 - a. Apply clear curing and sealing compound for integrally colored concrete according to manufacturer's instructions using manufacturer's recommended application techniques.
 - b. Apply curing and sealing compound at consistent time for each pour to maintain close color consistency.
3. Take precautions in hot weather to prevent plastic cracking resulting from excessively rapid drying at surface as described in NRMCA CIP 5.
4. Do not cover concrete with plastic sheeting.
5. There shall be no free water on surface at time of application.

D. Protection of Finished Work.

1. Prohibit foot or vehicular traffic on paving surface for the time specified by manufacturer, or until paving is properly protected from damage.
2. Barricade area to protect paving.
3. Protect paving surface from damage until final inspection and acceptance by Engineer.
4. Repair damaged colored concrete in accordance with manufacturer's instructions.

157188.04 METHOD OF MEASUREMENT.

Colored Portland cement concrete pavement shall be measured by the square yard as shown in the contract documents. The area of manholes, intakes, or other fixtures in the pavement will not be deducted from the measured pavement area.

157188.06 BASIS OF PAYMENT.

Colored Portland cement concrete pavement shall be paid by the contract unit price per square yard. This shall include all labor, materials, equipment, and transportation required to install colored Portland cement concrete pavement.